


Lumirror 10.78

Application

- PE extrusion and lamination after surface primarization



PLAIN SYMMETRICAL PET FILM

Benefits

- Low amount of oligomers
- Low shrinkage at high temperature
- Excellent mechanical properties
- Specific micro-roughness on both sides

Typical Values *(These values do not constitute binding specifications)*

Properties	Test Method	Unit	12 µm
YIELD			
Unit Weight		g/m ²	16.8
Area Yield		m ² /kg	59.5
MECHANICAL			
Tensile Strength MD/TD	ASTM D 882	daN/mm ²	23/25
Elongation at Break MD/TD		%	116/98
THERMAL			
Shrinkage 150°C 30mn MD/TD	Internal Method	%	1,4/0,2
Shrinkage 200°C 30mn MD/TD			4/0,7
OPTICAL			
Gardner Haze	ASTM D1003	%	3
BARRIER			
Roughness Rz	Internal Method		29
Roughness Ra			282

Regulation

Lumirror® 10.78 complies with European applicable requirements for food contact applications. For Toray's certification concerning specific applications with each product, please refer to the 'Declaration of Compliance'.

Presentation of the rolls

Roll packaging: The rolls are suspended on standard paper core with internal diameter of 152.8mm. For all presentation, minimum roll width = 340mm and maximum roll width = 2100mm.

Returnable packaging: Wooden flanges, plastic flanges and pallets are returnable.

Please contact us for...

- Any other presentation (width, length, core)
- Process for returnable packaging
- Any other information about typical values, measuring conditions, tolerances, deliveries...

Lumirror® is a registered trademark of Toray Films Europe SAS - TFE January 2018

DISCLAIMER: This leaflet is provided for informational purpose only and is not binding, nor can it constitute specifications to the buyer. The information contained in this document is based on numerous tests and trials we have carried out in our laboratories. Deviations from the results thus obtained can therefore be experienced depending on the actual conditions of use. This document does not provide any guarantee with regard to compliance of our product with the typical values indicated, nor does it provide any guarantee as the suitability of our products for any particular use.