


# Lumirror® 60.61

## Application

- Electrical insulation
- Mold release
- Release liner



WHITE OPAQUE  
PET FILM

## Benefits

- White opaque
- High dimensional stability
- Good flatness
- UL 94 VTM-2
- UL 746B (105°C)

## Typical Values *(These values do not constitute binding specifications)*

Properties	Test Method	Unit	23 µm	36 µm	50 µm	75 µm	125 µm	150 µm	190 µm	250 µm
<b>YIELD</b>										
Unit Weight		g/m <sup>2</sup>	32.1	51.8	72	108	180	215	273.6	360
Area Yield		m <sup>2</sup> /kg	30.2	19.3	13.9	9.26	5.55	4.65	3.65	2.78
<b>MECHANICAL</b>										
Tensile Strength MD	ASTM D 882	daN/mm <sup>2</sup>	19	19	20	22	22	20	21	19
Elongation at Break MD		%	136	146	126	124	132	140	150	184
<b>THERMAL</b>										
Shrinkage 150°C 30mn MD/TD	Internal Method	%	1.5/0.1	1.4/0	1.5/0.1	2.0/0.9	1.7/0.6	1.4/0.1	1.4/0.5	1.4/0.4
<b>OPTICAL</b>										
Total Light transmittance	ASTM D1003	%	80	75	68	54	51	46	43	40
<b>SURFACE</b>										
Roughness Ra	Internal Method	nm	30	30	32	43	39	38	35	33
Roughness Rz			342	353	350	704	717	600	719	837
<b>ELECTRICAL</b>										
Break down voltage	ASTM D149	kV	*	*	*	*	*	*	17	*
Volume resistivity	ASTM D257	Ω	*	*	*	*	*	*	5*10 <sup>16</sup>	*

## Regulation

Lumirror® 60.61 does **not** comply with European applicable requirements for food contact applications. For Toray's certification concerning specific applications with each product, please refer to the 'Declaration of Compliance'. Lumirror® 60.61 is in accordance with UL 94 VTM2 and with UL 746B (105°C) at 190µm.

## Presentation of the rolls

**Roll packaging:** The rolls are suspended on standard paper core with internal diameter of 152.8mm. For all presentation, minimum roll width = 340mm and maximum roll width = 2100mm.

**Returnable packaging:** Wooden flanges, plastic flanges and pallets are returnable.

## Please contact us for...

- Any other presentation (width, length, core)
- Process for returnable packaging
- Any other information about typical values, measuring conditions, tolerances, deliveries...

Lumirror® is a registered trademark of Toray Films Europe SAS - TFE March 2020

**DISCLAIMER:** This leaflet is provided for informational purpose only and is not binding, nor can it constitute specifications to the buyer. The information contained in this document is based on numerous tests and trials we have carried out in our laboratories. Deviations from the results thus obtained can therefore be experienced depending on the actual conditions of use. This document does not provide any guarantee with regard to compliance of our product with the typical values indicated, nor does it provide any guarantee as the suitability of our products for any particular use.