


Lumirror 10.51

Application

- Pre-cut lids
 - Dairy
 - Security



GLOSSY OPAQUE WHITE PET FILM WITH ONE COEXTRUDED SIDE

Benefits

- High gloss and white aspect
- Enhanced adhesion on the treated side
- Resistance to thermal treatment
- High dimensional and thermal stability

Typical Values *(These values do not constitute binding specifications)*

Properties	Test Method	Unit	12 µm	23 µm	36 µm
YIELD					
Unit Weight		g/m ²	17.3	33.1	51.8
Area Yield		m ² /kg	57.8	30.2	19.3
MECHANICAL					
Tensile Strength MD	ASTM D 882	daN/mm ²	18	17	20
Tensile Strength TD			21	21	21
Elongation at Break MD	ASTM D 882	%	110	120	115
Elongation at Break TD			75	85	95
THERMAL					
Shrinkage 150°C 30mn MD	Internal Method	%	1.7	1.6	1.8
Shrinkage 150°C 30mn TD			0.7	0.4	0.7
OPTICAL					
Total Light transmission	ASTM D1003		54	42	33
Gloss 60°	ASTM D523	%	103	103	100
White index	ASTM E313		92	91	95
SURFACE					
Roughness Ra	Internal Method	nm	30	30	30
Roughness Rz			300	300	300


Regulation

Lumirror® 10.51 complies with European legal requirements of food contact applications due to its specific treatment. For Toray's certification concerning specific applications with each product, please refer to the 'Declaration of Compliance'.

Presentation of the rolls

Roll packaging: The rolls are suspended on standard paper core with internal diameter of 152.8mm. For all presentation, minimum roll width = 340mm and maximum roll width = 3400mm.

Returnable packaging: Wooden flanges, plastic flanges and pallets are returnable. The coextruded side is identified on the roll label.



Please contact us for...

- Any other presentation (width, length, core)
- Process for returnable packaging
- Any other information about typical values, measuring conditions, tolerances, deliveries...

Lumirror® is a registered trademark of Toray Films Europe SAS - TFE September 2020

DISCLAIMER: This leaflet is provided for informational purpose only and is not binding, nor can it constitute specifications to the buyer. The information contained in this document is based on numerous tests and trials we have carried out in our laboratories. Deviations from the results thus obtained can therefore be experienced depending on the actual conditions of use. This document does not provide any guarantee with regard to compliance of our product with the typical values indicated, nor does it provide any guarantee as the suitability of our products for any particular use.