


# Lumirror 10.50

## Application

- Pre-cut lids
  - Dairy
- Siliconising



GLOSSY OPAQUE WHITE  
SYMMETRICAL PET FILM

## Benefits

- High gloss
- Permanent white aspect
- High dimensional stability

## Typical Values *(These values do not constitute binding specifications)*

Properties	Test Method	Unit	50 µm
<b>YIELD</b>			
Unit Weight		g/m <sup>2</sup>	73.50
Area Yield		m <sup>2</sup> /kg	13.6
<b>MECHANICAL</b>			
Tensile strength MD	ASTM D 882	daN/mm <sup>2</sup>	20
Tensile strength TD			22
Elongation at Break MD	ASTM D 882	%	115
Elongation at Break TD			95
<b>THERMAL</b>			
Shrinkage 150°C 30mn MD	Internal Method	%	1.8
Shrinkage 150°C 30mn TD			0.6
<b>OPTICAL</b>			
Total Light transmission	ASTM D1003		25
Gloss 60°	ASTM D523	%	85
White index	ASTM E313		91
<b>SURFACE</b>			
Roughness Ra	Internal Method	nm	55
Roughness Rz			600

## Regulation

Lumirror® 10.50 complies with European applicable requirements for food contact applications. For Toray's certification concerning specific applications with each product, please refer to the 'Declaration of Compliance'.

## Presentation of the rolls

**Roll packaging:** The rolls are suspended on standard paper core with internal diameter of 152.8mm. For all presentation, minimum roll width = 340mm and maximum roll width = 2100mm.

**Returnable packaging:** Wooden flanges, plastic flanges and pallets are returnable.

## Please contact us for...

- Any other presentation (width, length, core)
- Process for returnable packaging
- Any other information about typical values, measuring conditions, tolerances, deliveries...

Lumirror® is a registered trademark of Toray Films Europe SAS - TFE September 2020

**DISCLAIMER:** This leaflet is provided for informational purpose only and is not binding, nor can it constitute specifications to the buyer. The information contained in this document is based on numerous tests and trials we have carried out in our laboratories. Deviations from the results thus obtained can therefore be experienced depending on the actual conditions of use. This document does not provide any guarantee with regard to compliance of our product with the typical values indicated, nor does it provide any guarantee as the suitability of our products for any particular use.